

ZHANJIANG CHENMING

EUCA HB

2018.2

GSM		215	235	275	325	365
ITEM						
Basis Weight	g/m ²	210-215	230-235	270-275	320-325	360-365
Caliper	um	310±10	350±10	415±10	490±10	555±10
Stiffness (MD/CD)	mN. m	≥4.5/2 .6	≥8.5/3.8	≥13.0/7. 0	≥21.0/9. 5	27.7/14.0
Roughness	um	1.0-1.5				
Folding Endurance	Times	25-40				
Moisture	%	Summer 8.0-8.6 Winter 8.3-8.9		Summer 8.3-8.9 Winter 8.6-9.2		
Gloss	%	45-50				
Ink absorption	%	20-25				
Whiteness	%	91.5±1.5				
Surface Printing Intensity	m/s	2.0-2.5				
Internal Bond Strength	J/m ²	130-180				