

CHENMING ART FBB SPECIFICATION

Grammage	g/m^2	210 \pm 3	230 \pm 3	250 \pm 3	300 \pm 5	350 \pm 5	400 \pm 5
Thickness	μm	280 \pm 10	310 \pm 10	345 \pm 10	420 \pm 10	490 \pm 10	555 \pm 10
Stiffness	m N. m	5.5/3.0	8.0/4.0	9.2/4.5	16.0/9.0	29.0/13.5	38.5/16.5
Brightness	%	90.0-92.0					
Gloss	%	55-60					
Roughness	μm	1.0-1.5					
Moisture	%	6.0-6.5					
Plybond	J/m^2	120-220					
Bulk	%	1.35-1.45					