



CONDAT GLOSS SHEET *



WEIGHT	90	100	110	115	120	130	135	150	170	200	225	250	275	300	350	380
THICKNESS	68	76	84	87	92	96	100	114	133	152	176	195	215	240	295	320
BULK	0.76	0.76	0.76	0.76	0.77	0.74	0.74	0.76	0.78	0.76	0.78	0.78	0.78	0.80	0.84	0.84
WHITENESS CIE D65	121	121	121	121	121	121	121	121	121	121	121	121	121	121	121	121
OPACITY	89	91	92.5	93	94.5	95.5	96	97	98	-	-	-	-	-	-	-
PAPER GLOSS	75	75	75	75	75	78	78	78	78	79	79	79	79	79	79	79
SMOOTHNESS	2300	2000	1900	2100	1800	1800	1800	1300	850	1000	800	700	600	600	350	300
mini :	1600	1200	800	700	600	600	600	600	400	500	400	350	300	300	200	150
REL. HUMIDITY 23°C	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%

Property	Standard	Units	Tolerance
Weight	ISO 536	gsm	+ / - 4%
Bulk	ISO 534	cm3/gr	
Thickness	ISO 534	microns	+ / - 7%
Whiteness CIE D65	ISO 11475	Index	+ / - 3 pts
Opacity	ISO 2471	%	+ / - 2 pts
Paper Gloss	TAPPI T-480	%	+ / - 5 pts
Smoothness	ISO 5627	sec	
Relative Humidity	TAPPI T-502	%	+ / - 10 pts



* Those specifications are subject to change without prior notice